

SPRAYMAX

1K ACRYLIC PRIMER FILLER - MEDIUM GRAY




Application: Acrylic filler with good stability, fast drying time and excellent dry-sanding properties. Ideal for spot repairs. Can be used on steel, galvanized steel, aluminum and various plastics.

Advantages: Excellent filling properties. Sag resistant. Excellent dry-sanding properties. Recoatable with all standard solvent-/ water borne basecoats or single stage topcoats.



SPRAY PASS
2 - 3 spray passes,
each approx. 0.8 mil



FLASH-OFF TIME
5 min
Top coat in 10-15 min / 68°F



DRYING INFRARED DEVICE
15 min / 68°F
IR: 3 min



SANDING WET/DRY MANUALLY
P400 - P500
P800

PROD NO.	DESCRIPTION	BX QTY
3680282	1K Acrylic Primer Filler	3/bx

2K WASH PRIMER




Application: 2K primer for fast insulation of sanded through areas as part of car repair paintwork. For cleaned and sanded surfaces such as steel, aluminum, hardened surfaces, 2K body fillers and old paintwork.

Advantages: Very good adhesion. Excellent anti-corrosion protection, in particular on aluminum. Must be recoated with 2K Urethane Acrylic Filler. Fast drying. (Do not overcoat with water-based paints or 2K epoxy primer surfacers. Do not overcoat with 2K UP putties.)




SPRAY PASS
1 - 2 spray passes,
0.4 - 0.6 mil



FLASH-OFF TIME
5 min



DRYING
10 min / 68°F



2K POTLIFE
96 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3684029	2K Wash Primer	3/bx

2K RAPID PRIMER FILLER - GRAY, NON-ISOCYANATE




Application: Universal, quick-drying 2K primer for high quality automotive paint jobs. Ideal for partial paint jobs and spot repair.

Advantages: Free from isocyanates and resistant to solvents. Quick drying (1 hour at 68°F). Good sandability. High filling capacity (up to 4 mil). Excellent adhesion, including on bare sheet and galvanized surfaces as well as existing sanded paint finishes. Recoatable with all standard solvent/water borne basecoats or single stage topcoats.



SPRAY PASS
2 - 3 spray passes,
each approx. 1.2 mil




FLASH-OFF TIME
5-10 min
Top coat in 20 min
/ 68°F



DRYING
60 min / 68°F
30 min / 140°F
IR: 15 min



SANDING WET/DRY MANUALLY
P400 - 500
P800 - 1200




2K POTLIFE
24 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3680031	2K Rapid Primer Filler	3/bx

2K EPOXY PRIMER - BEIGE 2K EPOXY PRIMER - GRAY 2K EPOXY PRIMER - BLACK



SPRAY PASS
2 - 3 spray passes,
each 1.2 - 1.4 mil




FLASH-OFF TIME
5 min.
Top coat in
15 min-12 hours / 68°F



DRYING INFRARED DEVICE
12 hours / 68°F
30 min / 120°F
IR: 20 min



SANDING WET/DRY
MANUALLY
P400 - 500
P800 - 1200



2K POTLIFE
4 days / 68°F

PROD NO.	DESCRIPTION	BX QTY
3680032	2K Epoxy Primer - Beige	3/bx
3680033	2K Epoxy Primer - Gray	3/bx
3680034	2K Epoxy Primer - Black	3/bx

2K POLYESTER FILLER




Application: The 2K Polyester Filler is a peroxide activated filler in an aerosol can for a very fast repair of rough surface structures. (e.g. Hail- Dents, rough metal structures, deep sanding marks, orange peel structures, pin holes; others). Ready for use - no manual mixing of Polyester Filler with peroxide needed. Perfectly suitable for leveling surfaces!

Advantages: Very long potlife compared to conventional sprayable polyester. Filler (2-6h depending on surrounding temperatures). Film build 8-28mil is possible. Fast drying 1-5h at room temperature / IR 30min.. Easy to sand (very hard surface). Needs to be primed before coating.



SPRAY PASS
2 - 5 spray passes,
4 - 18 mil




FLASH-OFF TIME
5 min



DRYING
2 - 4 hours / 68°F
IR: 30 min



SANDING WET/DRY
MANUALLY
P180 - 500



2K POTLIFE
6 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3684026	2K Polyester Filler	3/bx

SPRAYMAX

1K TRIM PAINT - BLACK SATIN




Application: For high-quality topcoat paint jobs and spot repairs on cars, motorcycles and other applications.

Advantages: Easy to use. High yield. Excellent coverage due to high solid matter content. Dries quickly. Very good flow.



SPRAY PASS
2 - 3 spray passes,
each 0.6 - 0.8 mil



FLASH-OFF TIME
1 - 5 min / 68°F



DRYING INFRARED DEVICE
3 hours / 68°F
30 min / 140°F
IR: approx. 7 min

PROD NO.	DESCRIPTION	BX QTY
3680102	1K Trim Paint - Satin Black	3/bx

2K HOT ROD BLACK SATIN




Application: For small damage repair jobs on existing semi gloss Hot Rod Back parts/surfaces or for an easy and fast paint job of a newer restored part.

Advantages: Easy to use. High quality two component coating. Very good flow. Highest chemical and weather resistance. Long lasting and very durable finish.




SPRAY PASS
2 - 3 spray passes,
each approx. 1 mil



FLASH-OFF TIME
25 min / 68°F



DRYING INFRARED DEVICE
3 hours / 68°F
35 min / 140°F



2K POTLIFE
24 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3680212	2K Hot Rod Black	3/bx




1K CLEAR ACRYLIC

Application: 1K clear coat for quick coating and longterm sealing of repair paint jobs and new paint jobs on cars and motorcycles.

Advantages: Easy to use. Dries quickly. High gloss level. No color deviation. Good weathering resistance. Very good flow. Very good polishing ability.



SPRAY PASS
2 - 3 spray passes,
each 0.6 - 0.8 mil



FLASH-OFF TIME
5 - 10 min / 68°F



DRYING INFRARED DEVICE
12 hours / 68°F
60 min / 140°F
IR: approx. 7 min

PROD NO.	DESCRIPTION	BX QTY
3680058	1K Clear Acrylic	3/bx




2K CLEAR GLAMOUR

Application: 2K clear coat with very high chemical, gasoline, and weather resistance for high-quality and long-term sealing of repair paint jobs and new paint jobs on cars and motorcycles.

Advantages: Maximum resistance to abrasion and scratching. Very smooth flow. Lasting high gloss. Very good polishing ability. No color deviation. Outstanding painting surface. Suitable even at higher ambient temperatures.




SPRAY PASS
2 spray passes,
each 0.6 - 0.8 mil



FLASH-OFF TIME
5 - 10 min / 68°F



DRYING INFRARED DEVICE
18 hours / 68°F
60 min / 140°F
IR: approx. 15 min



2K POTLIFE
48 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3680061	2K Clear Glamour	3/bx




2K CLEAR RAPID

Application: 2K clear coat with very short drying time and very high chemical, gasoline and weathering resistance for high quality and longterm sealing of repair paint jobs and new paint jobs on cars and motorcycles. Ideally suited for spot repairs.

Advantages: Very fast drying. Very smooth flow. Lasting high gloss. Maximum resistance to abrasion and scratching. No color deviation. Outstanding painting surface. Very good polish ability. Suitable even at lower ambient temperatures. Ideally suited for small surfaces.



SPRAY PASS
2 spray passes,
each 0.6 - 0.8 mil



FLASH-OFF TIME
5 min / 68°F



DRYING INFRARED DEVICE
60 min / 68°F
30 min / 140°F
IR: approx. 15 min



2K POTLIFE
14 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3684064	2K Clear Rapid	3/bx

SPRAYMAX

2K CLEAR MATTE



Application: Developed for the Small Damage Repair Process or complete painting of mounting parts.
Advantages: Very fast drying. Excellent flow. Highest chemical and weathering resistance.
 Gloss units @ 85°: Matte 12±3



SPRAY PASS
 2 spray passes,
 each 0.6 - 0.8 mil



FLASH-OFF TIME
 5 - 10 min / 68°F



DRYING INFRARED DEVICE
 18 hours / 68°F
 60 min / 140°F
 IR: approx. 15 min



2K POTLIFE
 48 hours / 68°F

PROD NO.	DESCRIPTION	BX QTY
3680065	2K Clear Matte	3/bx

1K SPOT BLENDER



Application: 1K Spot Blender is a special product for homogeneous paint transitions in the blending area of 2K clearcoats as well as of single stage topcoats with outstanding blending results. The Spot Blender is used immediately after the clear- / topcoat is applied.

Advantages: Seamless edge transitions in the blending area. Superior blending ability. No color deviations. Ideal for spot repairs.



SPRAY PASS
 2-3 very light
 spray passes

PROD NO.	DESCRIPTION	BX QTY
3680093	1K Spot Blender	3/bx

GUN CLEANER



Application: Rich in active cleaning solvents for the thorough cleaning of the variator nozzle or conventional spray guns.

Advantages: Suitable for solvent and waterborne basecoats. Equipped with lancet. Cleans variator nozzle.



PROTECTIVE GLOVES



PROTECTIVE EYEWEAR

PROD NO.	DESCRIPTION	BX QTY
3680095	Gun Cleaner	3/bx