



## RUBBERIZED UNDERCOAT #20-46 Black

A paintable undercoating for all vehicle undercarriages. Forms a rubberized skin that reduces road noise and protects metal from salt corrosion and road debris. Dries fast and does not sag. Does not 'bleed-thru' when topcoated.

### Suggested Uses:

Panel & fender undersides  
 Hoods & decks  
 Trunk interiors  
 Section repairs  
 Weld joints  
 Rust holes  
 All chassis parts

### Packaging:

UPC Code	043281005203
Cans per case	12
Shipping weight per case	19.6 lbs.
Container	20 fluid ounce can
Label weight	18 ounces (511 grams)
Shipping Classification	limited quantity, UN 1950
Hazard Class	2.1

### Properties:

Flammability	"Extremely Flammable"
Flash point	-40 F
Specific Gravity	0.80
Solids Content	~60%
VOC content	~39%, cannot exceed 40%
MIR value	~0.99
HAPs content	18%
Storage Temperature	40-90F
Application Temperature	50-100F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	3000 F
Gasoline Resistance	No
Resin System	Petroleum Asphalt
Shelf life	Guaranteed for 2 years

### Dry Time\*:

To touch	10 minutes
To handle	6 hours

\*At 720 F, 50% humidity,  
 1.5 mil thickness

\*\*Curing/Recoat time is extended with  
 multiple coats and excessively thick  
 coats\*\*

**Gloss\*:** Low Lustre, 15-25

\*as measured on a 600 gloss meter

12-2-2021